

Patent Abstracts of Japan

PUBLICATION NUMBER : 63069204
PUBLICATION DATE : 29-03-88

APPLICATION DATE : 10-09-86
APPLICATION NUMBER : 61211466

APPLICANT : C I KASEI CO LTD;

INVENTOR : FUJII KAZUMASA;

INT.CL. : H01F 1/02 C08K 3/00 C08K 5/54 C08L 23/26

TITLE : COMPOSITE FOR MAGNET

ABSTRACT : PURPOSE: To increase flexibility, resistance to shock, resistance to solvent attack, etc. by compounding silicone oil in a mixture of acid anhydride modified ethylene-butene copolymer resin and polyolefin resin.

CONSTITUTION: 12~25 pts. wt. resin mixture composed of 50~90 wt. % acid anhydride modified ethylene-butene copolymer resin A and 50~100 wt. % polyolefin resin B, and 88~75 pts. wt. ferromagnetic powder are so compound that the sum amount becomes 100 pts. wt. 1~10 pts. wt. silicone oil is compounded in 100 pts. wt. the above composition. The resin A is obtained by graft polymerization of unsaturated acid anhydride in the ethylene-butene copolymer containing, for example, ethylene unit and butene unit in the range of weight ratio 1:9~9:1. The resin B is polyethylen, polypropylene, etc. Thus, flexibility, resistance to shock, resistance to solvent attack, etc. can be increased.

COPYRIGHT: (C)1988,JPO&Japio